



# NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898  
http://www.nypla.com

## Product Information

## NYLOY<sup>®</sup> MG-1113B

- Nylon 66
- 13% Glass Fiber Reinforced/Impact Modified
- Black

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	psi	10384.07
Elongation	ASTM D638	%	3
Flexural Strength	ASTM D790	psi	16073.97
Flexural Modulus	ASTM D790	psi	526315.79
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	2.84
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	R-94
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
264 psi		°F	383
66 psi		°F	-
<b>OTHER</b>			
Density	ASTM D792	lb/in <sup>3</sup>	0.0363
Mold Shrinkage	ASTM D955		-
Normal		%	1.08
Parallel		%	0.78
Moisture Contents	-	%	-
<b>REMARK</b>			
(1) This data is for reference only.			