



# NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898

<http://www.nypla.com>

## Product Information

## NYLOY<sup>®</sup> M-0030N-V N1-1

- Nylon 66
- Non-Halogen Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	kg/cm <sup>2</sup> (MPa)	760 (74.58)
Elongation	ASTM D638	%	13
Flexural Strength	ASTM D790	kg/cm <sup>2</sup> (MPa)	1100 (107.95)
Flexural Modulus	ASTM D790	kg/cm <sup>2</sup> (MPa)	3.30x10 <sup>4</sup> (3238.47)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	4.0 (39.22)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	R-117
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm <sup>2</sup> ) (1.82MPa)		°C	-
(4.6kg/cm <sup>2</sup> ) (0.46MPa)		°C	-
<b>OTHER</b>			
Density	ASTM D792	g/cm <sup>3</sup>	1.169
Mold Shrinkage	ASTM D955		-
Normal		%	1.32
Parallel		%	1.28
Moisture Contents	-	%	-
Flammability	UL-94	1.6mm	V0
	UL-94	3.2mm	-
<b>REMARK</b>			
(1) This data is for reference only.			