



NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898

<http://www.nypla.com>

Product Information

NYLOY[®] M-0030N-V N1-1

- Nylon 66
- Non-Halogen Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	MPa	77
Elongation	ISO 527	%	13
Flexural Strength	ISO 178	MPa	114
Flexural Modulus	ISO 178	MPa	3000
Charpy Impact, Notched 23° C	ISO 179/ 1eA	kJ/m ²	3.2
Charpy Impact, Notched -20° C	ISO 179/ 1eA	kJ/m ²	-
Hardness Rockwell R Scale	ISO 2039	-	-
Hardness Shore D	ISO 868	-	-
THERMAL			
Heat Deflection Temp	ISO 75		
1.82MPa		°C	-
0.46MPa		°C	-
OTHER			
Density	ISO 1183	g/cm ³	1.17
Mold Shrinkage	ISO 294-4		-
Normal		%	1.32
Parallel		%	1.28
Ash Content	-	%	-
Flammability	UL-94	1.6mm	V0
	UL-94	3.2mm	-
REMARK			
(1) This data is for reference only.			