



NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898
http://www.nypla.com

Product Information

NYLOY[®] M-0030N-V N4

- Nylon 66
- Non-Halogen Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	830 (81.45)
Elongation	ASTM D638	%	10
Flexural Strength	ASTM D790	kg/cm ² (MPa)	1250 (122.67)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	3.50x10 ⁴ (3434.74)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	3.0 (29.41)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	R-118
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	-
(4.6kg/cm ²) (0.46MPa)		°C	-
OTHER			
Density	ASTM D792	g/cm ³	1.170
Mold Shrinkage	ASTM D955		-
Normal		%	1.38
Parallel		%	1.44
Moisture Contents	-	%	-
Flammability	UL-94	1.6mm	V0
	UL-94	3.2mm	-
REMARK			
(1) This data is for reference only.			