



NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898
http://www.nypla.com

Product Information

NYLOY[®] M-0030N-V N4-1

- Nylon 66
- Non-Halogen Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	11522.05
Elongation	ASTM D638	%	10
Flexural Strength	ASTM D790	psi	17496.44
Flexural Modulus	ASTM D790	psi	497866.29
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	0.55
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	R-118
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	-
66 psi		°F	-
OTHER			
Density	ASTM D792	lb/in ³	0.0363
Mold Shrinkage	ASTM D955		-
Normal		%	1.38
Parallel		%	1.44
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	V0
	UL-94	1/8 in	-
REMARK			
(1) This data is for reference only.			