



# NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898  
http://www.nypla.com

## Product Information

## NYLOY<sup>®</sup> M-0030N-V N4-1

- Nylon 66
- Non-Halogen Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ISO 527	MPa	79
Elongation	ISO 527	%	10
Flexural Strength	ISO 178	MPa	115
Flexural Modulus	ISO 178	MPa	3200
Charpy Impact, Notched 23° C	ISO 179/ 1eA	kJ/m <sup>2</sup>	3.2
Charpy Impact, Notched -20° C	ISO 179/ 1eA	kJ/m <sup>2</sup>	-
Hardness Rockwell R Scale	ISO 2039	-	-
Hardness Shore D	ISO 868	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ISO 75		
1.82MPa		°C	-
0.46MPa		°C	-
<b>OTHER</b>			
Density	ISO 1183	g/cm <sup>3</sup>	1.17
Mold Shrinkage	ISO 294-4		-
Normal		%	1.38
Parallel		%	1.44
Ash Content	-	%	-
Flammability	UL-94	1.6mm	V0
	UL-94	3.2mm	-
<b>REMARK</b>			
(1) This data is for reference only.			