NYPLA INDUSTRIAL CO., LTD.
TEL: 626-6264889 FAX: 626-6264898
http://www.nypla.com

Product Information

NYLOY® MG-8030N-V 60BK1

● Nylon 66 ● 34% Glass Fiber Reinforced / Non-Halogen Flame Retardant ● Black

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	18492.18
Elongation	ASTM D638	%	1.3
Flexural Strength	ASTM D790	psi	26315.79
Flexural Modulus	ASTM D790	psi	1365576.1
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	1.1
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	455
66 psi		°F	-
OTHER			
Density	ASTM D792	lb/in^3	0.0448
Mold Shrinkage	ASTM D955		-
Normal		%	1.06
Parallel		%	0.38
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	V0
	UL-94	1/8 in	-
REMARK			
(1) This data is for reference only.			