



# NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898  
http://www.nypla.com

## Product Information

## NYLOY<sup>®</sup> NS-0600N

- Nylon 6
- Impact Modified
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	7112.38
Elongation	ASTM D638	%	150
Flexural Strength	ASTM D790	psi	10668.56
Flexural Modulus	ASTM D790	psi	256045.52
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	14.68
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	-
66 psi		°F	-
OTHER			
Density	ASTM D792	lb/in <sup>3</sup>	-
Mold Shrinkage <sup>(2)</sup>	ASTM D955	x10 <sup>-3</sup> in/in	22-26
Moisture Contents	-	%	0.2
Flammability	UL-94	1/16 in	HB
	UL-94	1/8 in	-
REMARK			
<sup>(1)</sup> This data is for reference only.			
<sup>(2)</sup> Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			