



NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898
http://www.nypla.com

Product Information

NYLOY[®] NS-0300N

• Nylon 6 • Impact Modified • Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	400 (39.25)
Elongation	ASTM D638	%	150
Flexural Strength	ASTM D790	kg/cm ² (MPa)	530 (52.01)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	1.43x10 ⁴ (1403.34)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	105.0 (1029.41)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	D-68
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	-
(4.6kg/cm ²) (0.46MPa)		°C	-
OTHER			
Density	ASTM D792	g/cm ³	1.051
Mold Shrinkage	ASTM D955		-
Normal		%	1.61
Parallel		%	1.21
Moisture Contents	-	%	-
REMARK			
(1) This data is for reference only.			