



NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898
<http://www.nypla.com>

Product Information

NYLOY[®] NS-0300N

• Nylon 6 • Impact Modified • Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	5689.9
Elongation	ASTM D638	%	150
Flexural Strength	ASTM D790	psi	7539.12
Flexural Modulus	ASTM D790	psi	203413.94
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	19.27
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	D-68
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	-
66 psi		°F	-
OTHER			
Density	ASTM D792	lb/in ³	0.0326
Mold Shrinkage	ASTM D955		-
Normal		%	1.61
Parallel		%	1.21
Moisture Contents	-	%	-
REMARK			
(1) This data is for reference only.			