



NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898
http://www.nypla.com

Product Information

NYLOY® NG-1020NM

- Nylon 6
- 20% Glass Fiber Reinforced/Impact Modified
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	840 (82.43)
Elongation	ASTM D638	%	3
Flexural Strength	ASTM D790	kg/cm ² (MPa)	1300 (127.58)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	4.45x10 ⁴ (4367.03)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	32 (313.73)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	R-115
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	200
(4.6kg/cm ²) (0.46MPa)		°C	-
OTHER			
Density	ASTM D792	g/cm ³	1.206
Mold Shrinkage	ASTM D955		-
Normal		%	1
Parallel		%	0.58
Moisture Contents	-	%	-
REMARK			
(1) This data is for reference only.			