



# NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898  
http://www.nypla.com

## Product Information

## NYLOY<sup>®</sup> NG-1020NM

- Nylon 6
- 20% Glass Fiber Reinforced/Impact Modified
- Natural

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	psi	11948.79
Elongation	ASTM D638	%	3
Flexural Strength	ASTM D790	psi	18492.18
Flexural Modulus	ASTM D790	psi	633001.42
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	5.87
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	R-115
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
264 psi		°F	392
66 psi		°F	-
<b>OTHER</b>			
Density	ASTM D792	lb/in <sup>3</sup>	0.0374
Mold Shrinkage	ASTM D955		-
Normal		%	1
Parallel		%	0.58
Moisture Contents	-	%	-
<b>REMARK</b>			
(1) This data is for reference only.			