



# NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898  
http://www.nypla.com

## Product Information

## NYLOY<sup>®</sup> NF-0040N

• Nylon 6 • 40% Mineral Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	kg/cm <sup>2</sup> (MPa)	900 (88.32)
Elongation	ASTM D638	%	1.5
Flexural Strength	ASTM D790	kg/cm <sup>2</sup> (MPa)	1400 (137.39)
Flexural Modulus	ASTM D790	kg/cm <sup>2</sup> (MPa)	9.00x10 <sup>4</sup> (8832.19)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	4.6 (45.1)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	R-116
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm <sup>2</sup> ) (1.82MPa)		°C	-
(4.6kg/cm <sup>2</sup> ) (0.46MPa)		°C	-
<b>OTHER</b>			
Density	ASTM D792	g/cm <sup>3</sup>	1.470
Mold Shrinkage	ASTM D955		-
Normal		%	1.01
Parallel		%	0.71
Moisture Contents	-	%	-
<b>REMARK</b>			
(1) This data is for reference only.			