



NYPLA INDUSTRIAL CO., LTD.

TEL:909-7843888 FAX:909-7843889
http://www.nypla.com

NYLOY[®] N-0020N-V0

Product Information

- Nylon6
- Flame Retardant
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	750 (73.5)
Elongation	ASTM D638	%	10
Flexural Strength	ASTM D790	kg/cm ² (MPa)	1100 (107.8)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	30000 (2941.2)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	4.0 (39.2)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	-
(4.6kg/cm ²) (0.46MPa)		°C	-
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
OTHER			
Density	ASTM D792	g/cm ³	1.17
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ mm/mm	0.7~1.4
Moisture Contents	-	%	-
Flammability	UL-94	1.6mm	V2
	UL-94	3.2mm	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			