



NYPLA INDUSTRIAL CO., LTD.

TEL:909-7843888 FAX:909-7843889
http://www.nypla.com

NYLOY[®] MG-0025N-V0

Product Information

- Nylon66
- Glass Fiber Reinforced/Flame Retardant
- White

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	1300 (127.4)
Elongation	ASTM D638	%	2
Flexural Strength	ASTM D790	kg/cm ² (MPa)	1900 (186.3)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	85000 (8333.3)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	7.5 (73.5)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	-
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	230
(4.6kg/cm ²) (0.46MPa)		°C	-
ELECTRICAL			
Arc Resistance	ASTM D495	sec	-
CTI,solution A	IEC 60112	-	-
OTHER			
Density	ASTM D792	g/cm ³	1.535
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ mm/mm	-
Moisture Contents	-	%	-
Flammability	UL-94	1.6mm	-
	UL-94	3.2mm	V0
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			