



NYPLA INDUSTRIAL CO., LTD.

TEL:909-7843888 FAX:909-7843889
http://www.nypla.com

NYLOY[®] XG-0033N-V0 HG30N4

- High Temp. Nylon
- Glass Fiber Reinforced / Halogen Flame Retardant
- Natural

Product Information

PROPERTIES	METHOD	UNIT	RESULT	
MECHANICAL				
Tensile Strength	ISO 527	MPa	130	
Elongation	ISO 527	%	1.5	
Flexural Strength	ISO 178	MPa	210	
Flexural Modulus	ISO 178	MPa	9400	
Charpy Impact, Notched 23° C	ISO 179/ 1eA	kJ/m ²	8	
THERMAL				
Heat Deflection Temp (18.6kg/cm ²)(1.82MPa)	ISO 75	°C	235	
OTHER				
Ash Contents	ISO 3451	%	GF 30	
Flammability	UL-94	1.6mm	V0	
	UL-94	0.8mm	-	
Density	ISO 1183	g/cm ³	1.61	
PHYSICAL				
Mold Shrinkage	ISO 294-4		-	
		Normal	%	0.8
		Parallel	%	0.35
FLAMMABILITY				
Glow Wire Test (GWFI)	IEC 60695-2-12	2.0mm	-	
Glow Wire Test (GWIT)	IEC 60695-2-13	2.0mm	-	
ELECTRICAL				
CTI (Solution A)	IEC 60112		-	
REMARK				
(1)This data is for reference only.				