



NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898
http://www.nypla.com

Product Information

NYLOY[®] GMG-0133B-2

- Nylon 66
- Glass Fiber Reinforced
- Black

Lot.No. : F2A2260026

PROPERTIES	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	1450 (142)
Elongation	ASTM D638	%	2.5
Flexural Strength	ASTM D790	kg/cm ² (MPa)	2250 (220)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	86000 (8425)
IZOD Impact, Notched 23° C	ASTM D256	kg-cm/cm (J/M)	10.0 (98)
IZOD Impact, Notched -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°C	-
OTHER			
Density	ASTM D792	g/cm ³	1.395
Mold Shrinkage	ASTM D955		
Normal, 2.0mm		%	-
Parallel, 2.0mm		%	-
Flammability	UL-94	1.6mm	-
REMARK			
(1) This data is for reference only.			

Moulding guide

Drying Temp.	C°	100~120
Drying Time	hr	2~4
Mold Temp.	C°	100~120
1 st inj.		
V(%) / P(%)	%	55/60
2 nd inj.		
V(%) / P(%)	%	50/45
3 rd inj.		
V(%) / P(%)	%	30/25
4 th inj.		
V(%) / P(%)	%	20/15
Nozzle Temp.	C°	270~290
1 st Barrel Temp.	C°	290~310
2 nd Barrel Temp.	C°	280~300
3 rd Barrel Temp.	C°	260~280
Cooling Time	Sec.	25

REMARK

This data-sheet is for reference only.