



NYPLA INDUSTRIAL CO., LTD.

TEL:909-7843888 FAX:909-7843889
<http://www.nypla.com>

Product Information

NYLOY[®] LG-0030N B1

- LCP
- Glass Fiber Reinforced
- Black

PROPERTIES	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ISO 527	kg/cm ² (MPa)	1530 (150)
Elongation	ISO 527	%	1.4
Flexural Strength	ISO 178	kg/cm ² (MPa)	2040 (200)
Flexural Modulus	ISO 178	kg/cm ² (MPa)	132653 (13000)
IZOD Impact, Notched 23° C	ISO 179	kJ/m ² (J/M)	10 (102)
IZOD Impact, Notched -20°C	ISO 179	kJ/m ² (J/M)	-
THERMAL			
Heat Deflection Temp (18.6kg/cm ²) (1.82MPa)	ISO 75	°C	270
OTHER			
Density	ISO 1183	g/cm ³	1.6
Mold Shrinkage Parallel, 2.0mm	ISO 294-4	%	0.15
REMARK			
(1) This data is for reference only .			

Moulding guide

Drying Temp.	°C	140-150
Drying Time	hr	4-12
Mold Temp.	°C	80-120
1 st inj.		
V(%) / P(%)	%	20/40
2 nd inj.		
V(%) / P(%)	%	20/35
3 rd inj.		
V(%) / P(%)	%	20/25
4 th inj.		
V(%) / P(%)	%	-
Nozzle Temp.	°C	340-360
1 st Barrel Temp.	°C	345-365
2 nd Barrel Temp.	°C	340-360
3 rd Barrel Temp.	°C	320-340
Cooling Time	Sec.	20
REMARK		
This data-sheet is for reference only .		