

**NYPLA INDUSTRIAL CO., LTD.**TEL: 626-6264889 FAX: 626-6264898
http://www.nypla.com

Product Information

NYLOY[®] UB-0010N G50L1N

• High Temp. Nylon • Glass Fiber Reinforced • Natural

PROPERTY	METHOD	UNIT	RESULT	
MECHANICAL				
Tensile Strength	ISO 527	MPa	210	
Tensile Modulus	ISO 527	MPa	-	
Elongation	ISO 527	%	2	
Flexural Strength	ISO 178	MPa	330	
Flexural Modulus	ISO 178	MPa	14500	
Charpy Impact, Notched 23° C	ISO 179	kJ/M ²	14	
THERMAL				
Heat Deflection Temp (18.6kg/cm ²)(1.82MPa)	ISO 75	°C	250	
OTHER				
Ash Contents	ISO 3451	%	GF 50	
Flammability	UL-94	1.6mm	-	
	UL-94	0.8mm	-	
Density	ISO 1183	g/cm ³	1.57	
PHYSICAL				
Mold Shrinkage	ISO 294-4		-	
		Normal	%	0.5
		Parallel	%	0.29
FLAMMABILITY				
Glow Wire Test(GWFI)	IEC 60695-2-12	2.0mm	-	
Glow Wire Test(GWIT)	IEC 60695-2-13	2.0mm	-	
REMARK				
(1)This data is for reference only.				