



NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898
http://www.nypla.com

Product Information

TOYOLAC 900

- ABS
- Transparent
- Medium Impact Strength

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	psi	5974.4
Elongation	ASTM D638	%	40
Flexural Strength	ASTM D790	psi	9103.84
Flexural Modulus	ASTM D790	psi	263157.89
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	2.94
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	-
Hardness Rockwell R Scale	ASTM D785	-	R-108
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
264 psi		°F	177.8
66 psi		°F	-
OTHER			
Density	ASTM D792	lb/in ³	0.0335
Mold Shrinkage ⁽²⁾	ASTM D955	x10 ⁻³ in/in	4-6
Moisture Contents	-	%	-
Flammability	UL-94	1/16 in	HB
	UL-94	1/8 in	-
REMARK			
⁽¹⁾ This data is for reference only.			
⁽²⁾ Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			