



# NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898  
http://www.nypla.com

## Product Information

## NYLOY<sup>®</sup> MS-0100B-10

• Nylon 66 • Impact Modified • Black

PROPERTY	METHOD	UNIT	RESULT
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	psi	6000
Elongation	ASTM D638	%	90
Flexural Strength	ASTM D790	psi	8500
Flexural Modulus	ASTM D790	psi	230000
IZOD Impact, Notched 1/8" 73.4°F	ASTM D256	ft-lb/in	16
IZOD Impact, Notched 1/8" -4°F	ASTM D256	ft-lb/in	9.5
Hardness Rockwell R Scale	ASTM D785	-	R-102
Hardness Shore D	ASTM D2240	-	-
<b>THERMAL</b>			
Heat Deflection Temp	ASTM D648		
264 psi		°F	140
66 psi		°F	-
<b>OTHER</b>			
Density	ASTM D792	lb/in <sup>3</sup>	0.0335
Mold Shrinkage <sup>(2)</sup>	ASTM D955	x10 <sup>-3</sup> in/in	18-24
Moisture Contents	-	%	0.2
<b>REMARK</b>			
<sup>(1)</sup> This data is for reference only.			
<sup>(2)</sup> Shrinkage parallel to flow. Test box dimensions of base(129×2.7×3.2) mm.			