



NYPLA INDUSTRIAL CO., LTD.

TEL: 626-6264889 FAX: 626-6264898
http://www.nypla.com

Product Information

NYLOY[®] MG-0033N

- Nylon 66
- 33%Glass Fiber Reinforced
- Natural

PROPERTY	METHOD	UNIT	RESULT
MECHANICAL			
Tensile Strength	ASTM D638	kg/cm ² (MPa)	1800 (176.64)
Elongation	ASTM D638	%	2
Flexural Strength	ASTM D790	kg/cm ² (MPa)	2700 (264.97)
Flexural Modulus	ASTM D790	kg/cm ² (MPa)	1.02x10 ⁵ (10009.81)
IZOD Impact, Notched 1/8" 23°C	ASTM D256	kg-cm/cm (J/M)	16.0 (156.86)
IZOD Impact, Notched 1/8" -20°C	ASTM D256	kg-cm/cm (J/M)	-
Hardness Rockwell R Scale	ASTM D785	-	R-115
Hardness Shore D	ASTM D2240	-	-
THERMAL			
Heat Deflection Temp	ASTM D648		
(18.6kg/cm ²) (1.82MPa)		°C	250
(4.6kg/cm ²) (0.46MPa)		°C	-
OTHER			
Density	ASTM D792	g/cm ³	1.380
Mold Shrinkage	ASTM D955		-
Normal		%	1.21
Parallel		%	0.43
Moisture Contents	-	%	-
REMARK			
(1) This data is for reference only.			